

SUBJECT Microbiological Test

TEST LOCATION TÜV SÜD China
TÜV SÜD 中国

TÜV SÜD Products Testing (Shanghai) Co., Ltd.
南德商品检测（上海）有限公司
B-3/4, No.1999 Du Hui Road, Minhang District
Shanghai 201108, P.R. China
中国.上海闵行区都会路 1999 号 B 幢 3/4 楼
邮编:201108

CLIENT NAME ASUSTeK Computer Inc.

CLIENT ADDRESS No.15, Lide Rd., Beitou Dist.,Taipei City 112,Taiwan

**IDENTIFICATION/
MODEL NO(s)** LCD monitor Item No.:VY229 series & VY279 series

TEST PERIOD 18-Jul-2023~02-Aug-2023

TEST REQUEST Antibacterial Test- according to ISO 22196:2011



Prepared By

范诗宇

(Fan Shiyu)
Report Drafter

Authorized By

张创

(Zhang Chuang)
Authorized Signatory

Note: (1) General Terms & Conditions as mentioned overleaf. (2) The results relate only to the items tested.(3) The test report shall not be reproduced except in full without the written approval of the laboratory.(4) Without the agreement of the laboratory , the client is not authorized to use the test results for unapproved propaganda.


SAMPLE SOURCE /RECEIPT DATE/ TEST DATE

Logistics Express / 18-Jul-2023/18-Jul-2023

THE FOLLOWING SAMPLE(S) WAS/WERE SUBMITTED

BY/ ON BEHALF OF THE CLIENTS AS:

Sample Name: ABF-0200E,K26212
Identification/Model No(s): LCD monitor Item No.:VY229 series & VY279 series
Sample Specification: /
Batch No./Date: /
Manufacturer: /

SAMPLE NO.	DESCRIPTION	PHOTOGRAPH
721682649	Black sheet	

TEST METHOD(S)

Antibacterial Test
- according to ISO 22196:2011 Measurement of antibacterial activity on plastics and other non-porous surfaces

TEST ORGANISM(S)

Escherichia coli ATCC 8739
Staphylococcus aureus ATCC 6538P

TEST RESULT(S)

Name of test bacteria	Concentration of bacteria (CFU/mL)	The average(cells/cm ²) of the common Logarithm of the number of viable bacteria recovered			Log value of antimicrobial activity
		/	at "0h" contact time	at "24h" contact time	
<i>Escherichia coli</i> ATCC 8739	6.6 ×10 ⁵	Sample	/	-0.2	6.8
		Control Sample	3.9	6.6	
<i>Staphylococcus aureus</i> ATCC 6538P	5.7 ×10 ⁵	Sample	/	-0.2	5.9
		Control Sample	3.9	5.7	

Note:

- The control sample is provided by TÜV SÜD laboratory.
- Preparation of test specimens by wiping with 70% ethanol in water.
- The volume of the test inoculum used is 0.2 mL. The surface area of the cover film is 1600 mm².
- 0.05% Polysorbate80 was added to the test inoculum.
- This report replaces report 721682649, 721682649 is obsolete
- Comment: PASS. Limit is provided by client, with reference to JIS Z 2801: If the value of antibacterial activity more than 2.0 indicates the tested product with antibacterial effectiveness.

-END OF THE TEST REPORT-